

CONTOPP®

NANOSILIN 20Z

Adolf-Oesterheld-Str.1
D-97337 Dettelbach
Tel: +49(0)9324/9199-0
info@knopp-chemie.com
knopp-chemie.com

PROPERTIES

PRODUCT DESCRIPTION

- For firm adhesion and anchoring of adhesives on the cement surface.
- For filling and sealing small cracks in the cement surface.
- Increase tensile strength in the entire cross-section of the penetration depth (up to 3 cm).
- Increase pull-up strength.

APPLICATION AREA

- Saponification-resistant hardening of cement surfaces.
- Suitable for synthetic- and cement-based adhesives.

TECHNICAL DATA

CHARACTERISTICS

Colour:	reddish
Form:	liquid
Density (at 20 °C):	1.12 ± 0.02 g/ml
Processing temperature:	from + 5 °C up to 25 °C
Shelf life:	approx. 12 months – protect from frost and direct sunlight
Supply form:	Disposable container: PE-HD-can: 20 kg total Reusable container: Container: 1000 kg total

PROCESSING INFORMATION

BASE PREPARATION

- For CONTOPP® Nanosilin 20Z, the cement-bonded base must be absorbent (porous), load bearing, fine-grained, free from silt, dust and loose parts (if necessary, these must be removed using an industrial vacuum); it must also be free from oil, grease and other impurities that could have a separating effect.
- Nature of construction and construction site preparation following BS 8204-1 and 8000.

PROCESSING

- Undiluted depending on the absorptive capacity of the base, spray about 100 – 300 g/m² on the screed surface.
- Application can take place using a hose, roller or brush.
- The hardener CONTOPP® Nanosilin 20Z does not form a film – it is open porous.
- Try out a test area in order to check if a sufficiently deep hardening is being achieved.

FOLLOW-UP TREATMENT

- A subsequent coating of CONTOPP® Nanosilin 20Z can take place after 24 hours drying time.
- Adhesives containing solvents may only be applied after the complete reaction and drying. Carry out a hair hygrometer test in accordance with BS 8203 or the CM (Carbide Bomb) measurement according to the European standards.
- It is possible to further process using PU-based systems!

COMPATIBILITY WITH CONTOPP® PRODUCTS

CONTOPP® Nanosilin 20Z can be used with all products of the CONTOPP® series that have been used in overlay and underlay surfaces.

GENERAL INFORMATION

SAFETY

- Always observe general work hygiene when using our products.
- CONTOPP® hardeners are solvent-free, chloride-free, and safe in terms of organic architecture.
- Our products do not deteriorate when stored properly. Therefore, stability and reactivity are not affected by storage.
- You can find out more information on handling CONTOPP® hardeners from our safety data sheets.

STANDARDS AND TESTING REGULATIONS

- BS 8203: Installation of resilient floor coverings
- BS 8204: In-situ floorings – bases and screeds
- BS 8000: Code of practice for cement/sand floor screeds and concrete floor toppings

COMMENTS

The raw materials we process and the products we produce are subject to strict factory inspections. Do not use products from other manufacturers when using this product. It is stressed that our products and the procedure must be tested for suitability for the expected construction site conditions. The quality of screeds is essentially influenced by the quality of sand and cement, the mixing rates and the processing in accordance with approved screeding technology. Upon the publication all other previous copies shall become invalid.

Last updated: 24.09.2026